

EP1560 Putty

Dutch Resin Group BV
Gladsaxe 19
7327JZ
Apeldoorn
Netherlands
Tel: +31 55 312 44 65
Email: sales@dutchresin.nl
Web: www.dutchresin.nl

Product description

The EP1560 filler from Dutch Resin Group is a 2-component, solvent-free filler based on epoxy resin.

Product details

Packaging size	Set size
5 kg	A-component 4.44 kg B-component 0.56 kg
Appearance	Glossy
Colour	Natural
Shelf life	12 months after the production date when stored at normal temperature (15 °C). See more under <i>storage</i>

Product features

- Glossy appearance
- Simple application
- Solvent-free
- High strength
- Good mechanical load capacity

Areas of application

- Wood rot repair
- Filling cracks in the floor
- Filling holes in the floor
- Smoothing transition strips
- Create raised edges

Technical specifications

Similar mass (density)	1.59 kg/d m ³
Mixing ratio	89.0 A Weight 11.0 B Weight
Consumption	N/A
Processing time	Approximately 30 minutes. *
Dust dry	After 8 hours *
Walkable	After 4 PM *
Recoatable	After 16 hours, apply the next layer within 36 hours.
Fully loadable	7 days
Adhesion strength (n/mm ²)	>1.5
Viscosity (mPa.S)	3000 – 4000
Shore Hardness	>D80

At normal temperature of 20°C.

Product processing conditions

Subsurface temperature	Minimum 10°C, maximum 30°C, Optimal 20°C
Ambient temperature	Minimum 10°C, maximum 30°C, Optimal 20°C
Subsurface moisture content	Moisture < 4%
Relative humidity	Maximum 75% RH
Dew point	at least 3°C above the dew point. Complete curing cannot occur with large temperature fluctuations towards the freezing point.
Pay attention	These conditions apply to both the processing and curing of the product. Ensure adequate ventilation in the room.

Work and environmental protection

Storage and shelf life

Solvent-free. Non-flammable. Component A: Contains epoxy resin: Irritant. Component B: Contains amine hardener: Corrosive.

Both components: Irritation or burns of the eyes, respiratory organs, and skin possible.

Sensitization is possible through skin contact. In case of contact with skin, wash immediately with plenty of water and soap. In case of contact with eyes, rinse immediately with water and consult a doctor. Wear suitable protective gloves and safety glasses during handling. Environmentally hazardous in liquid state; therefore, do not allow to enter the sewer, open water, or soil. Hazard/safety instructions on the can label and the Safety Data Sheet must be observed, among others. After curing, odorless and ecologically and physiologically safe.

Removal of material

Uncured product residues. Do not allow to enter sewers, open water, or soil. These uncured components are chemical waste. Cured components are classified as construction waste.

The product must be stored dry at temperatures of a minimum of 10 and a maximum of 25 degrees. Under these conditions, the shelf life of an unopened package is at least 12 months. Very rarely, crystallization may occur in the epoxy resin at low temperatures; this crystallization can be easily reversed by heating the package and its contents before use.

Subsurface preparation

Remove cement and concrete residue by grinding and sanding the floor.

Roughen dense substrates such as concrete by dust-free blasting. Roughen anhydrite floors by blasting or sanding. Treat contaminated substrates by chemically cleaning them and then sanding them. Always make the floor dust-free by vacuuming with an industrial vacuum cleaner.

Plaster alternative

The primer EP1100 can be mixed with Sylothix setting agent to create a thick filler.